

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 006 238 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
07.06.2000 Bulletin 2000/23

(21) Application number: 99122106.0

(22) Date of filing: 05.11.1999

(51) Int. Cl.⁷: **D21H 23/42**, D21H 17/66
// F24F3/14, (D21H13/36,
17:65, 17:66)

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:-
AL LT LV MK RO SI

(30) Priority: 01.12.1998 SE 9804152

(71) Applicant: Proflute AB
186 30 Vallentuna (SE)

(72) Inventor: Aronson, Per-Johan
191 46 Sollentuna (SE)

(74) Representative:
Bergstrand, Mikael Gudmundsson
Albhlms Patentbyrå Stockholm AB
P.O. Box 5581
114 85 Stockholm (SE)

(54) Method of impregnating paper

(57) A method of impregnating paper with water-glass, such as soda waterglass or potassium silicate, said impregnated paper being usable as a dehumidifying element, wherein the method comprises the steps of

- a) providing paper sheet (18,36), such as facing paper and/or corrugated paper;
- b) immersing the paper (18,36) into a highly concentrated waterglass solution (14,32) at a temperature within the range of 45-95°C, with said highly concentrated waterglass solution (14,32) having a viscosity of at least 350 mPa.s at a temperature of 45°C; and without drying
- c) cooling (20,38) the immersed paper (18,36) with air at a temperature of 35°C at the highest and preferably at a highest temperature of 25°C.

The two paper webs (18,36) may be joined (40,42) to form an impregnated corrugated paperboard (44).




FIG. 1

EP 1 006 238 A1

Description

[0001] The present invention relates to the dehumidification of air with the aid of a dehumidifying element that comprises a fibre matrix which has been impregnated with waterglass. More specifically, the invention relates to a method of producing dehumidification elements.

TECHNICAL BACKGROUND

[0002] Air is normally dehumidified with the aid of a dehumidifying element that can be fabricated by joining together a flat and a pleated fibre material that has moisture absorbing properties to form a laminate which is rolled into the form of a rotor or stacked in block form. A laminate of this nature is shown in Figure 3. The dehumidifying element can be said to resemble corrugated paperboard that has been rolled up to form a rotor, or corrugated board that has been cut into lengths and the lengths stacked together to form a block. This element includes a structure that has many mutually parallel passageways. The pleats are normally from 1.5 to 3 mm in height and the passageways have a length of from 50 to 400 mm. A sector of one such rotor is shown in Figure 4.

[0003] The initial roll or block is sawn and ground to form a rotor, which is often provided with a hub, spokes and/or cowling. The rotor forms the "heart" of an air dehumidifier, in which a fan or blower drives the air through the numerous rotor passageways. Because the walls of the passageways include a moisture absorbent, the air will be dry subsequent to passing through the rotor. A small heated air flow passes through a minor sector in the rotor and expels the moisture therefrom. Dry air is produced continuously, by continually rotating the rotor between the sections containing air to be dehumidified and sections through which heated air passes. The moisture extracted is carried away with the heated air flow in a separate passage system. This principle is illustrated in Figure 5.

[0004] SE,B,460 705 teaches a method of producing a dehumidifying element in which paper comprised of ceramic fibres is impregnated with a waterglass solution either prior to or subsequent to lamination, and in which the paper is heated after being impregnated and dried to form a hydrated waterglass having a water content of 3-20%. The resultant matrix is then submerged in acid, so as to form silica-hydrogel.

[0005] SE,B,460 021 teaches a humidifying element that consists of a laminate which comprises a sheet of ceramic fibres that is corrugated on one side and has a paper thickness of 0.18-0.25 mm, a wave length of 2.5-4.2 mm and a wave height of 1.5-2.3 mm. This laminate is impregnated with an active silicon dioxide-aluminium oxide-aerogel that comprises 97-85% silicon dioxide and 3-15% aluminium oxide. The element is produced by dipping ceramic paper into an aqueous solution of waterglass, and then dried. The element is then dipped into an aqueous solution of aluminium sulphate and again dried.

[0006] SE,B,462 671 describes a method of producing a dehumidifying element in which a laminate consisting of an undulating sheet and a flat sheet is impregnated with an aqueous solution of waterglass, followed by drying the laminate and heating the same to a water content of 5-45%, whereafter the laminate is dipped in an aqueous metal salt solution and finally dried and heated.

[0007] SE,B,469 976 describes a method of producing dehumidifying elements in which paper webs that include a shapeable material, such as glass fibre or cellulose, are drenched with concentrated waterglass solution and dried to a dry solids content of about 45-65% with respect to the waterglass, and then corrugated. The corrugated laminate is then dried to a dry solids content of about 60-95%.

[0008] EP,B,0,642,384 describes a method of treating dehumidifying elements with the purpose of influencing the pore size of the silica gel. This is achieved by treating the dehumidifying elements with acid, base and a stabilising solution that contains salts of zinc, aluminium and phosphate. It is also stated in this prior application that waterglass is applied to the paper and that the waterglass is then dried. All of the aforesaid documents describe an impregnating stage followed by a drying stage in conjunction with the preparation of dehumidifying elements that comprise a silica gel matrix.

[0009] Drying stages are energy consuming and therewith add to production costs. Furthermore, sufficient quantities of waterglass cannot be readily applied when the solution has the low concentration required by known technology. Consequently, the dehumidifying elements produced will have a limited amount of silica gel and the capacity of said elements will not be optimal. There is therefore a need for improved methods that lower production costs and raise the performance and quality of the end product.

SUMMARY OF THE INVENTION

[0010] It has been found that the drying stage that follows immersion of paper into the waterglass solution can be eliminated totally and that the amount of silica gel matrix applied can be increased at the same time, by applying a method that includes the steps of

- a) providing a paper sheet, such as a sheet of facing paper and/or undulated paper;
- b) submerging the paper in a highly concentrated waterglass solution at a temperature in the range of 45-95°C; and
- c) cooling the submerged paper with air at a temperature not higher than 35°C and preferably at 25°C at the highest.

Definitions

[0011] The term "waterglass" as used in this document refers to aqueous solutions of sodium silicate ("soda waterglass") or potassium silicate. Sodium waterglass and potassium silicate are often written as $(\text{Na}_2\text{O})_m(\text{SiO}_2)_n$ and $(\text{K}_2\text{O})_m(\text{SiO}_2)_n$ respectively, from which it will be seen that the mole ratio between the two oxides (n/m) can vary. In the case of the present invention, soda waterglass with n/m within the range of 3.3 to 3.4 is preferred, and waterglass with n/m from 3.2 to 3.4 is particularly preferred.

[0012] The expression "highly concentrated waterglass" as used in this document refers to waterglass that has a lower viscosity limit of at least 350 mPa.s at 45°C. The upper viscosity limit is 800 mPa.s at 95°C. The viscosity of highly concentrated waterglass at room temperature is so high as to make it extremely difficult to submerge paper in the waterglass and for the waterglass to wet the paper at this temperature. According to known technology, a typically concentrated waterglass at 20°C has a viscosity of up to 200 mPa.s. Highly concentrated waterglass, on the other hand, has a much greater viscosity at 20°C and in its least concentrated form can be likened to cold syrup or treacle.

[0013] The term "paper" as used in this document refers to sheets produced from organic fibres, such as cellulose, or inorganic fibres, such as ceramic fibres, glass fibres, slag fibres, carbon fibres and mineral fibres, and mixtures thereof. Inorganic fibres are preferred. It is also preferred to use glass fibres and/or mineral fibres in mixture with up to 20% cellulose fibres or synthetic fibres. The paper will typically have a thickness of 0.1-0.3 mm. The wave height of the undulating paper will typically be from 1-5 mm and the wave length typically from 1.5-7 mm. The paper will have a typical weight per unit area of 20-50 g/m².

DETAILED DESCRIPTION OF THE INVENTION

[0014] As mentioned earlier, the invention relates to a method of producing dehumidifying elements that comprise a paper matrix that has been impregnated with waterglass which is later converted to silica gel. Instead of using concentrated waterglass as a silica gel staffing material, there is used highly concentrated waterglass. This waterglass is so highly viscous as to render it practically impossible to impregnate paper at room temperature. However, the highly concentrated waterglass becomes fluid at temperatures of from 45-95°C and functions in the manner of concentrated waterglass. The paper that is to be impregnated is thus immersed into hot highly concentrated waterglass and then cooled with air having a temperature of 35°C at the highest, preferably at 25°C at the highest. It is not necessary to dry the paper. The cooled, impregnated paper also has good adhesive properties and can be easily joined to other paper.

[0015] Highly concentrated waterglass may be prepared, for instance, by evaporating off some of the water in concentrated waterglass, prior to manufacture.

[0016] When paper is impregnated conventionally with waterglass, the impregnated paper is heat-dried. In conjunction with this process, the waterglass becomes fluid and begins to run. There is no danger of this happening in the process according to the invention, since the highly concentrated waterglass solidifies or thickens in the cooling stage.

[0017] In the production of dehumidifying elements, the waterglass impregnated paper is dipped into a solution containing both acid and metal salt, wherewith the composition of the solution is chosen so that the product will obtain a high mechanical strength and a high dehumidifying capacity. SE-B-462 671 discloses examples of appropriate metal salts. Suitable acids are acids ranging from sulphuric acid to metal sulphates, phosphoric acid to metal phosphates, nitric acid to metal nitrates and hydrochloric acid to metal chlorides. A metal salt solution provides a gel of good stability. However, because a low pH is required in order to obtain a high moisture absorption capacity there is required a large salt surplus. Although the gel will have a high capacity when solely acid is used, the gel will readily break down when subjected to normal dehumidification processes.

[0018] The matrix obtained in these stages of manufacture is washed with water and dried to a finished product.

[0019] This process has many advantages. For instance, the process enables more waterglass to be applied per unit of surface area of the paper, since the highly concentrated waterglass is, of course, more concentrated than concentrated waterglass. This provides an end product whose moisture absorbing capacity is much greater than would otherwise be the case. It also results in a reduction in energy consumption, and therewith in production costs; since it is not necessary to dry the paper subsequent to its impregnation. Large quantities of energy are consumed in drying wet paper, since it is necessary to use either hot air or IR-lamps. Paper treated in accordance with the invention does not require the provision of expensive drying equipment. Finally, the product has better properties than known products, since there is no danger of the waterglass beginning to run after impregnation.

[0020] The invention will now be described in more detail with reference to the accompanying drawings.

Figure 1 illustrates schematically the principle of a process for manufacturing a dehumidification element in accordance with the invention.

Figure 2 is a diagram which includes equilibrium curves for dehumidifying element material. The moisture ratio (g absorbed water/100 g bone dry material) is plotted as a function of the relative humidity of material produced in accordance with the invention (A) on the one hand and for material produced in accordance with known technology (B) on the other hand.

Figure 3 shows a laminate consisting of facing paper and corrugated paper used in the manufacture of the rotor in an air dehumidifier.

Figure 4 illustrates a sector of the finished dehumidifying rotor. The rotor is comprised of a laminate of the kind shown in Figure 3, this laminate having been wound about a shaft in manufacturing the rotor; and

Figure 5 illustrates the working principle of a dehumidifying element. The air from which moisture shall be extracted is passed through passageways in a rotary dehumidifying element. Heated air is, at the same time, passed in counterflow through another sector of the rotating dehumidifying element.

[0021] The plant illustrated in Figure 1 includes paper rolls 10 and 28. A paper web taken from the roll 10 is led over a guide roller 12 down into a bath 14 that contains heated highly concentrated waterglass. Data for typical highly concentrated waterglass suitable for use in conjunction with this invention can be seen from Table 1 below.

Table 1

Examples of data for highly concentrated waterglass solutions	
Mole ratio $\text{SiO}_2/\text{Na}_2\text{O}$	3.3-3.4
Density (kg/dm ³)	1.41-1.45
Usable within the range	45-90°C
Optimal density (kg/dm ³)	1.43
Optimal temperature	70°C

[0022] Table 2 below sets forth two examples of highly concentrated waterglass solutions and their respective viscosities. The solutions are chosen to lie close to the viscosity limits applicable to highly concentrated waterglass solutions in accordance with the invention.

Table 2

Examples of data for two highly concentrated waterglass solutions		
	Example A	Example B
Mole ratio $\text{SiO}_2/\text{Na}_2\text{O}$	3.35	3.35
Density (kg/dm ³)	1.425	1.450
Viscosity	377 mPa:s at 45°C	800 mPa:s at 90°C

[0023] The paper web 18 is led down beneath the level of the highly concentrated hot waterglass solution in the bath 14 with the aid of a roller 16 submerged in the solution, said waterglass solution having a temperature of from 45-95°C. As the paper web 18 passes through the bath 14 the web is soaked with highly concentrated waterglass solution to a point of saturation. The saturated paper web is then passed up through a cooling chamber 20 in which air at room temperature is blown onto the web 18. The web 18 is then delivered via guide rollers 22 and 24 to a corrugating roll 26 to form a corrugated paper web that includes a large number of small pleats.

[0024] The corrugated paper, or undulated paper, will typically have a wave height of 1-5 mm and a wave length of 1.5-7 mm, as before mentioned. A second paper web 36 is taken from the paper storage roll 28 and delivered via a guide roll 30 to a bath 32 which contains heated highly concentrated water glass solution, into which the paper web 36 is immersed via a roller 34. The paper web 36 is there soaked and allowed to pass up through the cooling chamber 38, in which room temperature air is blown onto the web 36. The web 36 is passed from the cooling chamber 38, via a guide roller 40, to a combining roll 42 where the two paper webs 18 and 36 are joined to form an impregnated corrugated paperboard matrix. Because the impregnated paper webs 18 and 36 will readily adhere to one another after the cooling stage, no glue need be applied in joining said webs together.

[0025] The inventive process results in a matrix that contains from 10-25% more silica gel than matrices produced in accordance with known technology on the basis of the same type of paper, the same applied volume of waterglass, and the same type of matrix with respect to geometry and dimensions. This is illustrated in Figure 2, which shows two equilibrium curves for material in dehumidifying elements. Curve A refers to material produced in accordance with the invention, while curve B represents a material produced in accordance with SE 469 976. A prerequisite is that A and B have been produced from identical fibre paper as starting material and that the paper has been coated with equally thick layers of highly concentrated waterglass in respective curve A and typically concentrated waterglass in respective curve B.

Claims

1. A method of impregnating paper with waterglass, such as soda waterglass or potassium silicate, said impregnated paper being usable as a dehumidifying element, wherein the method comprises the steps of
 - a) providing paper sheet, such as facing paper and/or corrugated paper;
 - b) immersing the paper into a highly concentrated waterglass solution at a temperature within the range of 45-95°C, with said highly concentrated waterglass solution having a viscosity of at least 350 mPa.s at a temperature of 45°C; and
 - c) cooling the immersed paper with air at a temperature of 35°C at the highest and preferably at a highest temperature of 25°C.
2. A method according to Claim 1, characterised in that the highly concentrated waterglass solution has a viscosity of 800 mPa.s at the highest and a temperature of 95°C.
3. A method according to Claim 1 or 2, characterised in that the waterglass is soda waterglass.
4. A method according to Claim 3, characterised in that the mole ratio between SiO_2 and Na_2O in the soda waterglass is 3.2-3.5.
5. A method according to Claim 4, characterised in that the mole ratio between SiO_2 and Na_2O in the soda waterglass is 3.3-3.4.
6. A method according to any one of Claims 1-5, characterised in that the paper is produced from inorganic fibres, such as ceramic fibres, glass fibres, slag fibres, carbon fibres and mineral fibres, admixed with 0-20% cellulose fibres or synthetic fibres.
7. A method according to Claim 6, characterised in that the paper has a weight per unit area of 20-50 g/m².
8. A method according to any one of Claims 1-7, characterised in that after step c), the paper is dipped into an aqueous solution of a metal salt, such as aluminium sulphate, magnesium sulphate, primary aluminium phosphate ($\text{Al}_2\text{O}_3 \cdot 9\text{P}_2\text{O}_5$), magnesium chloride or aluminium nitrate, and an acid such as sulphuric acid, phosphoric acid, hydrochloric acid or nitric acid.
9. The use of a highly concentrated waterglass solution that has a viscosity of at least 350 mPa.s at a temperature of 45°C for impregnating paper in conjunction with the manufacture of dehumidifying elements.
10. The use according to Claim 9, characterised in that the highly concentrated waterglass solution has a viscosity of 800 mPa.s at the highest at a temperature of 95°C.




FIG. 1







FIG. 2





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 12 2106

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InCL7)
X	US 3 826 703 A (RUSSELL W) 30 July 1974 (1974-07-30) * column 4, line 16 - column 8, line 22; figures 1,5 *	1,3,4	D21H23/42 D21H17/66 //F24F3/14, D21H13:36, 17:65,17:66
Y	* the whole document *	1,9	
Y	US 5 423 934 A (VANGBO HAKAN ET AL) 13 June 1995 (1995-06-13) * the whole document *	1,9	
A		3,6,8	
D	& SE 469 976 B		
Y	US 4 411 216 A (MENSER HOWARD K) 25 October 1983 (1983-10-25) * the whole document *	1	
A		3,4	
A	US 4 911 775 A (KUMA TOSIMI ET AL) 27 March 1990 (1990-03-27) * the whole document *	1,3,6-9	
D	& SE 462 671 B		
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (InCL7)
			D21H
Place of search		Date of completion of the search	Examiner
MUNICH		8 February 2000	Nestby, K
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.92 (P/MC01)


ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 99 12 2106

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-02-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3826703 A	30-07-1974	DE 1960059 A	11-06-1970
		FR 2027572 A	02-10-1970
		NL 6918288 A	08-06-1970
		US 3616194 A	26-10-1971
US 5423934 A	13-06-1995	SE 469976 B	18-10-1993
		AU 2175192 A	25-01-1993
		DE 69225798 D	09-07-1998
		DE 69225798 T	19-11-1998
		EP 0590000 A	06-04-1994
		JP 6508314 T	22-09-1994
		SE 9101938 A	21-12-1992
US 4411216 A	25-10-1983	WO 9300220 A	07-01-1993
		NONE	
US 4911775 A	27-03-1990	JP 2013561 C	02-02-1996
		JP 5081831 B	16-11-1993
		JP 61252497 A	10-11-1986
		SE 462671 B	13-08-1990
		SE 8601546 A	23-10-1986



THIS PAGE BLANK (USPTO)